

## ENZINRON (ESD PA)

	METHOD	UNIT	VALUE
<b>Mechanical Properties</b>			
Specific gravity	ASTM D792	g/cm <sup>3</sup>	1.14
Tensile yield strength	ASTM D638	Mpa	70
Breaking elongation	ASTM D638	%	5
Bending strength	ASTM 790	Mpa	110
Flexural modulus	ASTM 790	Mpa	3900
Shore hardness	ASTM D2240	D	84
Impact strength	ASTM D256	J/M	102
<b>Thermal Properties</b>			
Melting point	DSC	°C	220
Heat distortion temperature	ASTM D648	°C	80
Operating temperature	-	°C	90
Maximum operating temperature	-	°C	155
Thermal conductivity	DIN 52612- 1	W/(K-M)	0.25
Coefficient of linear thermal	ASTM D696	10 <sup>-5</sup> - 1/K	7
<b>Electrical Properties</b>			
Dielectric strength	ASTM D150	KV-mm	-
Dielectric loss factor	ASTM D150	-	-
Volume resistivity	ASTM D257	Ω.cm	10 <sup>6-9</sup>
Surface resistivity	ASTM D257	Ω	10 <sup>6-9</sup>
Dielectric constant	ASTM D149	-	-
<b>Chemical Properties</b>			
Water absorption	23°C 60%RH	%	-
Acid resistance	23°C 60%RH		-
Alkali resistance			+
Acid and alkali resistance			+
Resistance to sodium chlorate			0
Resistance to aromatic compounds			+
Resistance to ketone	23°C 60%RH		+
Resistance to hot water	23°C 60%RH		+
<b>Others</b>			
Flammability	UL 94		HB
Viscosity	-		+

### Remarks:

- 1.“+”: positive “-”: negative “0”: depends.
2. All the parameters above are based on raw material but not finished products.