

ENZINRON (PP+30%GF)

	METHOD	UNIT	VALUE
Mechanical Properties			
Specific gravity	ASTM D792	g/cm ³	1.13
Tensile yield strength	ASTM D638	Mpa	40
Breaking elongation	ASTM D638	%	20
Bending strength	ASTM 790	Mpa	54
Flexural modulus	ASTM 790	Mpa	3000
Shore hardness	ASTM D2240	D	85
Impact strength	ASTM D256	J/M	35
Thermal Properties			
Melting point	DSC	°C	190
Heat distortion temperature	ASTM D648	°C	95
Operating temperature	-	°C	95
Maximum operating temperature	-	°C	120
Coefficient of linear thermal	ASTM D696	10 ⁻⁵ - 1/K	19
Electrical Properties			
Dielectric strength	ASTM D150	KV-mm	40
Volume resistivity	ASTM D257	Ω.cm	10 ¹⁴
Surface resistivity	ASTM D257	Ω	10 ¹³
Dielectric constant	ASTM D149	-	2.3
Chemical Properties			
Water absorption	23°C 60%RH	%	0.1
Acid resistance	23°C 60%RH		+
Alkali resistance			+
Acid and alkali resistance			+
Resistance to sodium chlorate			+
Resistance to aromatic compounds			-
Resistance to ketone	23°C 60%RH		+
Resistance to hot water	23°C 60%RH		+
Others			
Flammability	UL 94		HB
Viscosity	-		+
Non toxic	EEC 90/128 FDA		+
Coefficient of friction	DIN 53375		0.3
Anti-ultraviolet	-		0

Remarks:

1. "+": positive "-": negative "0": depends.
2. All the parameters above are based on raw material but not finished products.