

## ENZINRON (ABS+PC)

	METHOD	UNIT	VALUE
<b>Mechanical Properties</b>			
Specific gravity	ASTM D792	g/cm <sup>3</sup>	1.13
Tensile yield strength	ASTM D638	Mpa	55
Breaking elongation	ASTM D638	%	11
Bending strength	ASTM 790	Mpa	80
Flexural modulus	ASTM 790	Mpa	2000
Shore hardness	ASTM D2240	D	82
Impact strength	ASTM D256	J/M	150
<b>Thermal Properties</b>			
Melting point	DSC	°C	240
Heat distortion temperature	ASTM D648	°C	90
Operating temperature	-	°C	120
Maximum operating temperature	-	°C	145
Thermal conductivity	DIN 52612- 1	W/(K-M)	0.5
Coefficient of linear thermal	ASTM D696	10 <sup>-5</sup> - 1/K	8
<b>Electrical Properties</b>			
Dielectric strength	ASTM D150	KV-mm	27
Dielectric loss factor	ASTM D150	-	0.009
Volume resistivity	ASTM D257	Ω.cm	10 <sup>14</sup>
Surface resistivity	ASTM D257	Ω	10 <sup>16</sup>
Dielectric constant	ASTM D149	-	25.2
<b>Chemical Properties</b>			
Water absorption	23°C 60%RH	%	0.6
Acid resistance	23°C 60%RH		-
Alkali resistance			+
Acid and alkali resistance			+
Resistance to sodium chlorate			0
Resistance to aromatic compounds			+
Resistance to ketone	23°C 60%RH		+
Resistance to hot water	23°C 60%RH		+
<b>Others</b>			
Flammability	UL 94		HB
Viscosity	-		+
Non toxic	EEC 90/128 FDA		+
Coefficient of friction	DIN 53375		0
Anti-ultraviolet	-		-

### Remarks:

- 1.“+”: positive “-”: negative “0”: depends.
2. All the parameters above are based on raw material but not finished products.